

INTER-GUARD

Rust Proofing Wax Honey Coating

A fast drying wax-based barrier film which flows readily into cracks and seams to protect metals from rust and corrosion. One single coat offers longterm protection against weather and water. Will not crack, chip or peel. Will not attack copper, brass, steel or aluminum. Does not contain silicone. Can be used anywhere on the vehicle. Ideal for engine hood area, trunk and inner door compartments.

TECHNICAL DATA

Appearance	Opaque
Color	Dark Amber
Flammability:	"Extremely Flammable"
Flash Point:	-141°F / -96°C
Specific Gravity:	0.709
VOC Content:	81.92%
MIR Value:	1.03
Durability:	Excellent
Abrasion Resistance:	Excellent
Shelf Life:	1 year
Recommended film thickness:	4 - 5 mil
Gloss (as measured on a 60° gloss meter):	Flat, <15



- Superior Protective Rust Inhibitor
- Seeps Into Seams And Crevices
- Allows Material To Flow Into Hard To Reach Places
- Protects From Salts and Chemicals
- Resists Rock and Gravel Abrasion
- Weatherproof and Waterproof
- Highly Resistant To Heat With A Threshold of 100°C (212°F)
- Can Be Used Anywhere!

Applicable to the following specifications:

- Mil-C-83933A
- Mil-PFR 16173E, Grade 4, Class 1
- ASTM B117 - this product has been tested and can achieve over 1500 hours if you apply at a thickness of 4 mils (100 microns) dry film thickness.
- Wire Rope Field Dressing
- Acid Flume Resistance
- Outdoor Protection

DRY TIME*

To touch:	10 minutes
To recoat:	30 minutes
Hard Cure:	48 hours

*dry time may vary due to thickness, temperature and humidity

CAUTION

For professional use only. Before using this or any IES product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

STORAGE

Should be stored in a cool, dry location at a temperature between 60°F to 95°F (15°C to 35°C).

DIRECTIONS

1. Shake well before using. Wear safety glasses.
2. Surface should be clean, dry and free of grease, dirt and rust.
3. Hold can 10-12 inches from surface to be coated and apply a uniform coat over the entire area to be protected. Use the extension tube for hard to reach areas. For optimum rust protection, a 4 to 5 mil dry film thickness is recommended. This will usually require two passes.
4. Allow to dry for two to four hours before exposing to wet environmental conditions.
5. Do not spray on catalytic converter.
6. Clean valve after use by inverting can and spraying until free of material.

PRODUCT AVAILABLE

4557

20 oz. Aerosol Can
Net Weight 13.75 oz

12 per case

NOTICE TO PURCHASER: The following warranty is in lieu of all other expressed or implied warranties, specifically all goods are manufactured of first class materials and by competent professionals. We have no control over the use and application of our products. Our liability shall not exceed the purchase price.